Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2020-06-05-14** **Date: 16-12-19**
Customer	:	Assistant Executive Engineer, Doddabommasandra Sub Division, BBMP, Bangalore.
Address	:	Doddabommasandra Sub Division, BBMP, Bangalore.
Project Name	:	"Providing Missing covering Slabs at Muneshwar Block, subbanna Beedi in Ward No.10, (Doddabommasandra), Vidyaranyapura Sub division".
Agency	:	Sri Anjan L, #354, 5th Cross road, Sharadambanagara, Jalahalli (V), Banglore-560013
Customer's Reference	:	BBMP/EE/BTP/WO/172/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	13-12-19
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	14-12-19
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	2.1	_
2	Finess by Air permeablity method (m^2/kg,Min)	284.5	225m^2/kg, Min
3	Density (gm/cc)	3.13	_
4	Standard Consistency (%)	28%	Not specified
5	Initial Setting time	155 minutes	Not less than 30 minutes
6	Final Setting time	260 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	2mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore 97

AE W10

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2020-06-05-14** **Date: 11-01-20**
Customer	:	Assistant Executive Engineer, Doddabommasandra Sub Division, BBMP, Bangalore.
Address	:	Doddabommasandra Sub Division, BBMP, Bangalore.
Project Name	:	"Providing Missing covering Slabs at Muneshwar Block, subbanna Beedi in Ward No.10, (Doddabommasandra), Vidyaranyapura Sub division".
Agency	:	Sri Anjan L, #354, 5th Cross road, Sharadambanagara, Jalahalli (V), Banglore-560013
Customer's Reference	:	BBMP/EE/BTP/WO/172/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	13-12-19
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	14-12-19
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	28.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	39.0N/mm^2	Not less than 37 N/mm^2
3	28 Days	58.5N/mm^2	Not less than 53 N/mm^2

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Sumitha. NK
AE W10

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro
Sig.....
Date.....
BANGALORE

FOR CIVIL Pro.
R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2020-06-05-14** **Date: 16-12-19**
Customer	:	Assistant Executive Engineer, Doddabommasandra Sub Division, BBMP, Bangalore.
Address	:	Doddabommasandra Sub Division, BBMP, Bangalore.
Project Name	:	"Providing Missing covering Slabs at Muneshwar Block, subbanna Beedi in Ward No.10, (Doddabommasandra), Vidyaranyapura Sub
Agency	:	Sri Anjan L, #354, 5th Cross road, Sharadambanagara, Jalahalli (V), Banglore-560013
Customer's Reference	:	BBMP/EE/BTP/WO/172/2019-20
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	13-12-19
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	13-12-19

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : **15000 grams**

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	214	214	1.4	98.6	90-100
3	20 mm	7254	7468	49.8	50.2	30-70
4	10 mm	4442	11910	79.4	20.6	10-35
5	4.75 mm	2685	14595	97.3	2.7	0-5
6	Pan	405	15000	100.0	0	---

Sweetha.N.R
AE WIO

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2020-06-05-14** **Date: 16-12-19**
Customer	:	Assistant Executive Engineer, Doddabommasandra Sub Division, BBMP, Bangalore.
Address	:	Doddabommasandra Sub Division, BBMP, Bangalore.
Project Name	:	"Providing Missing covering Slabs at Muneshwar Block, subbanna Beedi in Ward No.10, (Doddabommasandra), Vidyaranyapura Sub division".
Agency	:	Sri Anjan L, #354, 5th Cross road, Sharadambanagara, Jalahalli (V), Banglore-560013
Customer Reference	:	BBMP/EE/BTP/WO/172/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	13-12-19
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	13-12-19

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	237	237	4.7	95.3	90-100
3	10 mm	2544	2781	55.6	44.4	25-55
4	4.75 mm	2107	4888	97.8	2.2	0-10
5	Pan	112	5000	100	0	_

Sweetha. N K
AE W10

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro
Sig.....
Date.....
BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2020-06-05-14** **Date: 16-12-19**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	10.7	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	11.4	
3	Specific Gravity	2.65	_
4	Bulk Density(Loose) (Kg/l)	1.53	_
5	Bulk Density(Compacted) (Kg/l)	1.57	_
6	Water Absorption(%)	0.19	_
7	Aggregate crushing Value(%)	25.6	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	22.5	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

CIVIL Pro Sig..... Date..... BANGALORE

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID	:	**CP-2020-06-05-14** **Date: 16-12-19**
Customer	:	Assistant Executive Engineer, Doddabommasandra Sub Division, BBMP, Bangalore.
Address	:	Doddabommasandra Sub Division, BBMP, Bangalore.
Project Name	:	"Providing Missing covering Slabs at Muneshwar Block, subbanna Beedi in Ward No.10, (Doddabommasandra), Vidyaranyapura Sub division".
Agency	:	Sri Anjan L, #354, 5th Cross road, Sharadambanagara, Jalahalli (V), Banglore-560013
Customer's Reference	:	BBMP/EE/BTP/WO/172/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	13-12-19
Sample Type	:	Fine Aggregate
Reference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
Date of test	:	13-12-19
Total weight taken	:	1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	27	27	2.7	97.3	90-100	90-100	90-100	95-100
3	2.36 mm	55	82	8.2	91.8	60-95	75-100	85-100	95-100
4	1.18 mm	239	321	32.1	67.9	30-70	55-90	75-100	90-100
5	600 micron	205	526	52.6	47.4	15-34	35-59	60-79	80-100
6	300 micron	203	729	72.9	27.1	5-20	8-30	12-40	15-50
7	150 micron	191	920	92.0	8.0	0-10	0-10	0-10	0-15
8	Pan	80	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

Sweetha. N R
AE W10

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL PRO Sig. Date. BANGALORE

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2020-06-05-14** **Date: 16-12-19**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.5	–
2	Specific Gravity	2.59	–
3	Material finer than 75 micron(%)	6.9	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Sweetha. NK
AE W10

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore-97

Format No: CP/TF/01

TEST RESULTS OF STEEL

Lab ID	:	**CP-2020-06-05-14** **Date: 16-12-19**
Customer	:	Assistant Executive Engineer, Doddabommasandra Sub Division, BBMP, Bangalore.
Address	:	Doddabommasandra Sub Division, BBMP, Bangalore.
Project Name	:	"Providing Missing covering Slabs at Muneshwar Block, subbanna Beedi in Ward No.10, (Doddabommasandra), Vidyaranyapura Sub division".
Agency	:	Sri Anjan L, #354, 5th Cross road, Sharadambanagara, Jalahalli (V), Banglore-560013
Customer's Reference	:	BBMP/EE/BTP/WO/172/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	13-12-19
Sample Type	:	Sunvik
Reference to BIS codes	:	IS 1786-2008, IS:1608-2005(RA 2011), IS 1599-2012.
Date of test:	:	13-12-19

Sl.No	Identification of sample	Grade of the sample	Diameter of the steel bar	Weight of the sample	Yield stress	Tensile strength	Elongation	Bend test	Rebend test
			(mm)	(kg/m)	(N/mm2)	(N/mm2)	(%)		
1	Sunvik	Fe500	8	0.391	512	652	20.0%	Satisfactory	Satisfactory
2	Sunvik	Fe500	10	0.616	528	672	20.0%	Satisfactory	Satisfactory
3	Sunvik	Fe500	12	0.888	544	668	20.0%	Satisfactory	Satisfactory

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

Suvetha. NK
AE W10

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore-97

CIVIL PRO BANGALORE
Sig.
Date

R RUDRAPRASAD
Authorized Signatory
Technical Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-05-14** **Date: 25/12/2019**

Customer : Assistant Executive Engineer, Doddabommasandra Sub Division, BBMP, Bangalore.

Address : Doddabommasandra Sub Division, BBMP, Bangalore.

Project Name : "Providing Missing covering Slabs at Muneshwar Block, subbanna Beedi in Ward No.10, (Doddabommasandra), Vidyaranyapura Sub division".

Agency : Sri Anjan L, #354, 5th Cross road, Sharadambanagara, Jalahalli (V), Banglore-560013

Customer's Reference : BBMP/EE/BTP/WO/172/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-12-19

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 25/12/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	18/12/2019	25/12/2019	149.62 X 149.25 X 150.46	22332	**8.415**	275.8	12.4	12.6
2	PCC	M15	18/12/2019	25/12/2019	151.85 X 151.81 X 150.72	23053	**8.558**	289.6	12.6	
3	PCC	M15	18/12/2019	25/12/2019	150.55 X 150.52 X 150.14	22661	**8.967**	289.4	12.8	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Sweetha. N L
AE W10

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP Bangalore-97

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2020-06-05-14** **Date: 15/01/2020**
Customer	:	Assistant Executive Engineer, Doddabommasandra Sub Division, BBMP, Bangalore.
Address	:	Doddabommasandra Sub Division, BBMP, Bangalore.
Project Name	:	"Providing Missing covering Slabs at Muneshwar Block, subbanna Beedi in Ward No.10, (Doddabommasandra), Vidyaranyapura Sub division".
Agency	:	Sri Anjan L, #354, 5th Cross road, Sharadambanagara, Jalahalli (V), Banglore-560013
Customer's Reference	:	BBMP/EE/BTP/WO/172/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-12-19
Customer ID	:	PCC
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M15 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	15/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	18/12/2019	15/01/2020	151.01 X 150.61 X 150.34	22743	**8.824**	406.8	17.9	17.4
2	PCC	M15	18/12/2019	15/01/2020	150.35 X 150.26 X 150.18	22591	**8.282**	390.3	17.3	
3	PCC	M15	18/12/2019	15/01/2020	151.22 X 151.54 X 149.32	22915	**8.298**	393.1	17.2	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Suvetha. N L
AE (10

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore : 97

CIVIL PRO BANGALORE
Sig.....
Date.....

FOR CIVIL Pro.
R RUDRAPRASAD
Authorized Signatory
Technical Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2020-06-05-14** **Date: 15/01/2020**
Customer	:	Assistant Executive Engineer, Doddabommasandra Sub Division, BBMP, Bangalore.
Address	:	Doddabommasandra Sub Division, BBMP, Bangalore.
Project Name	:	"Providing Missing covering Slabs at Muneshwar Block, subbanna Beedi in Ward No.10, (Doddabommasandra), Vidyaranyapura Sub division".
Agency	:	Sri Anjan L, #354, 5th Cross road, Sharadambanagara, Jalahalli (V), Banglore-560013
Customer's Reference	:	BBMP/EE/BTP/WO/172/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-12-19
Customer ID	:	PCC
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M15 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	15/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	18/12/2019	15/01/2020	150.86 X 149.92 X 151.61	22618	**8.824**	398.0	17.6	17.5
2	PCC	M15	18/12/2019	15/01/2020	151.40 X 151.84 X 151.36	22987	**8.282**	412.4	17.9	
3	PCC	M15	18/12/2019	15/01/2020	151.15 X 149.15 X 151.01	22545	**8.298**	384.1	17.0	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE W10

Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore-97

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	CP-2020-06-05-14 **Date: 29/12/2019**
Customer	:	Assistant Executive Engineer, Doddabommasandra Sub Division, BBMP, Bangalore.
Address	:	Doddabommasandra Sub Division, BBMP, Bangalore.
Project Name	:	"Providing Missing covering Slabs at Muneshwar Block, subbanna Beedi in Ward No.10, (Doddabommasandra), Vidyaranyapura Sub division".
Agency	:	Sri Anjan L, #354, 5th Cross road, Sharadambanagara, Jalahalli (V), Banglore-560013
Customer's Reference	:	BBMP/EE/BTP/WO/172/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	23-12-19
Customer ID	:	Drain Bottom Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	28/12/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Concrete	M20	21/12/2019	28/12/2019	150.22 X 150.54 X 150.55	22644	8.4	583	26	25.7
2	Drain Bottom Concrete	M20	21/12/2019	28/12/2019	150.22 X 150.54 X 150.55	22593	8.3	604	27	
3	Drain Bottom Concrete	M20	21/12/2019	28/12/2019	150.22 X 150.54 X 150.55	22455	8.4	553	25	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Sweetha N L
AE W10

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore-97

CIVIL Pro
Sig.
Date
BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-05-14** **Date: 18/01/2020**

Customer : Assistant Executive Engineer, Doddabommasandra Sub Division, BBMP, Bangalore.

Address : Doddabommasandra Sub Division, BBMP, Bangalore.

Project Name : "Providing Missing covering Slabs at Muneshwar Block, subbanna Beedi in Ward No.10, (Doddabommasandra), Vidyaranyapura Sub division".

Agency : Sri Anjan L, #354, 5th Cross road, Sharadambanagara, Jalahalli (V), Banglore-560013

Customer's Reference : BBMP/EE/BTP/WO/172/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 23-12-19

Customer ID : Drain Bottom Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M-20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Concrete	M20	21/12/2019	18/01/2020	151.02 X 151.37 X 150.20	22861	**8.435**	759.6	33.2	33.0
2	Drain Bottom Concrete	M20	21/12/2019	18/01/2020	150.48 X 151.18 X 149.94	22749	**8.460**	744.3	32.7	
3	Drain Bottom Concrete	M20	21/12/2019	18/01/2020	149.78 X 149.15 X 149.28	22340	**7.960**	739.0	33.1	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Suretha.N.K
AE 010

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore-97

CIVIL Pro
Sig.
Date
BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2020-06-05-14** **Date: 29/12/2019**
Customer	:	Assistant Executive Engineer, Doddabommasandra Sub Division, BBMP, Bangalore.
Address	:	Doddabommasandra Sub Division, BBMP, Bangalore.
Project Name	:	"Providing Missing covering Slabs at Muneshwar Block, subbanna Beedi in Ward No.10, (Doddabommasandra), Vidyaranyapura Sub division".
Agency	:	Sri Anjan L, #354, 5th Cross road, Sharadambanagara, Jalahalli (V), Banglore-560013
Customer's Reference	:	BBMP/EE/BTP/WO/172/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	23-12-19
Customer ID	:	Drain Bottom Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	28/12/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Concrete	M20	21/12/2019	28/12/2019	150.22 X 150.54 X 150.55	22852	8.0	589	26	25.8
2	Drain Bottom Concrete	M20	21/12/2019	28/12/2019	150.22 X 150.54 X 150.55	22549	8.5	602	27	
3	Drain Bottom Concrete	M20	21/12/2019	28/12/2019	150.22 X 150.54 X 150.55	22783	8.0	566	25	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Suvetha .N.K
AE U10

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore-97

CIVIL Pro
Sig.
Date.
BANGALORE

FOR CIVIL Pro.
R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2020-06-05-14** **Date: 18/01/2020**
Customer	:	Assistant Executive Engineer, Doddabommasandra Sub Division, BBMP, Bangalore.
Address	:	Doddabommasandra Sub Division, BBMP, Bangalore.
Project Name	:	"Providing Missing covering Slabs at Muneshwar Block, subbanna Beedi in Ward No.10, (Doddabommasandra), Vidyaranyapura Sub division".
Agency	:	Sri Anjan L, #354, 5th Cross road, Sharadambanagara, Jalahalli (V), Banglore-560013
Customer's Reference	:	BBMP/EE/BTP/WO/172/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	23-12-19
Customer ID	:	Drain Bottom Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M-20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	18/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Concrete	M20	21/12/2019	18/01/2020	151.85 X 151.01 X 149.73	22930	**8.422**	771.3	33.6	33.2
2	Drain Bottom Concrete	M20	21/12/2019	18/01/2020	149.15 X 149.32 X 150.77	22271	**8.371**	713.6	32.0	
3	Drain Bottom Concrete	M20	21/12/2019	18/01/2020	149.68 X 150.38 X 149.63	22508	**7.990**	764.8	34.0	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Sweetha. N L
AE W10

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

FOR CIVIL Pro.
R RUDRAPRASAD
Authorized Signatory
Technical Manager

CIVIL Pro Sig. Date BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2020-06-05-14** **Date: 03/01/2020**
Customer	:	Assistant Executive Engineer, Doddabommasandra Sub Division, BBMP, Bangalore.
Address	:	Doddabommasandra Sub Division, BBMP, Bangalore.
Project Name	:	"Providing Missing covering Slabs at Muneshwar Block, subbanna Beedi in Ward No.10, (Doddabommasandra), Vidyaranyapura Sub division".
Agency	:	Sri Anjan L, #354, 5th Cross road, Sharadambanagara, Jalahalli (V), Banglore-560013
Customer's Reference	:	BBMP/EE/BTP/WO/172/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	28-12-19
Customer ID	:	Drain Side Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	02/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	26/12/2019	02/01/2020	150.22 X 150.54 X 150.55	22521	8.2	577	26	25.5
2	Drain Side Wall Concrete	M20	26/12/2019	02/01/2020	150.22 X 150.54 X 150.55	22762	8.0	600	26	
3	Drain Side Wall Concrete	M20	26/12/2019	02/01/2020	150.22 X 150.54 X 150.55	22667	8.1	559	25	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Suvetha .N.L
AE WIO

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro
Sig.....
Date.....
BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-05-14** **Date: 23/01/2020**

Customer : Assistant Executive Engineer, Doddabommasandra Sub Division, BBMP, Bangalore.

Address : Doddabommasandra Sub Division, BBMP, Bangalore.

Project Name : "Providing Missing covering Slabs at Muneshwar Block, subbanna Beedi in Ward No.10, (Doddabommasandra), Vidyaranyapura Sub division".

Agency : Sri Anjan L, #354, 5th Cross road, Sharadambanagara, Jalahalli (V), Banglore-560013

Customer's Reference : BBMP/EE/BTP/WO/172/2019-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 28-12-19

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M-20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 23/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	26/12/2019	23/01/2020	151.94 X 150.90 X 150.81	22928	**8.333**	776.9	33.9	33.0
2	Drain Side Wall Concrete	M20	26/12/2019	23/01/2020	149.57 X 149.33 X 150.53	22335	**8.591**	715.4	32.0	
3	Drain Side Wall Concrete	M20	26/12/2019	23/01/2020	149.03 X 149.22 X 151.64	22239	**8.158**	737.8	33.2	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Surette. N L
AE WIO

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP Bangalore - 97

CIVIL Pro
Sig.
Date.
BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****